

Products: WS RIM Board

Western Structures Inc., 1381 Bailey Hill Road, PO Box 23355

Eugene, Oregon 97402

(541) 344-8878

www.westernstructures.com

1. Basis of the product report:
 - 2012 and 2009 International Building Code: Section 104.11 Alternative Materials
 - 2012 and 2009 International Residential Code: Section R104.11 Alternative Materials
 - ASTM D3737-08 and D3737-07 recognized by the 2012 IBC and IRC, and 2009 IBC and IRC, respectively
 - ANSI/AITC A190.1-07 recognized by the 2012 IBC and IRC, and 2009 IBC and IRC
 - ASTM D7672-11
 - APA Report T2011P-58 and other qualification data
2. Product description:

Western Structures WS RIM is used as rim boards and is manufactured with a proprietary specification. The source laminations are made of 2x4 Douglas-fir lumber end-jointed to form a long length in accordance with ANSI/AITC A190.1. The laminations are then face bonded to a specific beam depth up to 14 inches. The glulam is then resawn into WS RIM with net finished thickness of 1-1/2 inches. The maximum depth of WS RIM is 14 inches.
3. Design properties:

Table 1 lists the design properties for Western Structures WS RIM.
4. Product installation:

Western Structures WS RIM shall be installed in accordance with the recommendations provided by the manufacturer. Permissible field notching and drilling shall be in accordance with the recommendations provided by the manufacturer.
5. Fire-rated assemblies:

The provisions of IBC Section 721.6.3, Design of Fire-Resistant Exposed Wood Members, shall be applicable to Western Structures WS RIM. Fire-rated assemblies shall be constructed in accordance with the recommendations provided by APA Design/Construction Guide: *Fire-Rated Systems*, Form W305 (www.apawood.org/publications).
6. Limitations:
 - a) Western Structures WS RIM shall be designed in accordance with the applicable code using the design properties specified in this report.
 - b) Western Structures WS RIM shall be limited to 1-1/2 inches in thickness and a maximum of 14 inches in depth.
 - c) Western Structures WS RIM shall be limited to applications where the rim board is continuously supported for the full length and thickness of the product.
 - d) Western Structures WS RIM is limited to dry service conditions where the average moisture content of lumber is less than 16 percent.
 - e) Western Structures WS RIM is produced by Western Structures Inc. facility in Eugene, Oregon, under a quality assurance program audited by APA.
 - f) This report is subject to re-examination in one year.

7. Identification:

The WS RIM board described in this report are identified by a label bearing the manufacturer's name and/or trademark (Western Structures), the APA assigned plant number (1007), the product grade, the APA-EWS logo, the report number PR-L304, and a means of identifying the date of manufacture.

Table 1. Allowable Design Properties for Western Structures WS RIM ^(a,b)

Product	Thickness (in.)	Horizontal Load Transfer Capacity (lbf/ft) ^(c,d)	Vertical Load ^(e)			Lateral Resistance for 1/2-inch-dia. Lag Screws (lbf) ^(g)
			Uniform (lbf/ft)		Concentrated (lbf) ^(f)	
			Nails Spaced at 6 inches o.c.	Depths ≤ 11-7/8 in.	11-7/8 in. < Depth ≤ 14 in.	
WS RIM	1-1/2	240	3,000	2,800	2,500	410

For SI: 1 inch = 25.4 mm, 1 lbf = 0.454 kg, 1 psi = 6.9 kPa.

- ^(a) The rim board depth shall not exceed 14 inches. Only permitted in applications where the rim board is continuously supported for the full length and thickness of the product.
- ^(b) All design values are applicable to the normal load duration (10 years) for wood products, except for the horizontal load transfer capacity, which is based on the short-term load duration (10 minutes). Design values shall be adjusted for other load durations in accordance with the applicable building code except that the uniform vertical load capacity and concentrated vertical load capacity are not permitted to be increased for any load durations shorter than the normal load duration (10 years). The horizontal load transfer capacity is permitted to be increased by a factor of 1.4 when subjected to wind loads. Toe-nailed connections are not limited by the 150 lbf/ft lateral load capacity noted for Seismic Design Categories D, E and F in Section 4.1.7 of the Special Design Provisions for Wind and Seismic.
- ^(c) Western Structures WS RIM may be substituted for solid-sawn framing in horizontal wood diaphragms as shown in Table 2306.3.1 of the IBC, provided the maximum shear values for the diaphragms are limited to the allowable lateral capacity noted in this table.
- ^(d) 8d common (0.131x2-1/2 inch) nails shall be used to connect the floor sheathing to Western Structures WS RIM and to connect Western Structures WS RIM to the sill plate (toe nail). Two 8d box (0.113x2-1/2 inch) or common (0.131x2-1/2 inch) nails are required to connect each floor joist to the sill plate, and two 8d box (0.113x2-1/2 inch) or common (0.131x2-1/2 inch) nails are required to connect Western Structures WS RIM to the end of each floor joist.
- ^(e) Compression perpendicular-to-grain capacities of the sill plate and floor sheathing must be checked, and must not be exceeded.
- ^(f) The concentrated vertical load capacity is based on a 4-1/2-inch bearing length.
- ^(g) Capacity of lag screw connections between rim board and deck ledgers per lag screw of 1/2 inch in diameter when installed into the face of the WS RIM, 2x spruce-pine-fir side member, and 1/2-inch-thick sheathing with a full penetration of the WS RIM of the lag screw. Minimum end distance of 4 inches is required.

APA – *The Engineered Wood Association* is an accredited certification body under ISO 65 by Standards Council of Canada (SCC) and an accredited inspection agency by the International Code Council (ICC) International Accreditation Service (IAS) under ISO/IEC 17020. APA is also an accredited testing organization recognized by IAS and SCC under ISO/IEC 17025. APA is a recognized testing laboratory by Miami-Dade County, and a Product Testing Laboratory, Product Quality Assurance Entity, and Product Validation Entity by the Florida Department of Community Affairs (DCA).

APA – THE ENGINEERED WOOD ASSOCIATION

HEADQUARTERS

7011 So. 19th St. • Tacoma, Washington 98466

Phone: (253) 565-6600 • Fax: (253) 565-7265 • Internet Address: www.apawood.org

PRODUCT SUPPORT HELP DESK

(253) 620-7400 • E-mail Address: help@apawood.org

DISCLAIMER

APA Product Report® is a trademark of APA – *The Engineered Wood Association*, Tacoma, Washington. The information contained herein is based on the product evaluation in accordance with the references noted in this report. Neither APA, nor its members make any warranty, expressed or implied, or assume any legal liability or responsibility for the use, application of, and/or reference to opinions, findings, conclusions, or recommendations included in this report. Consult your local jurisdiction or design professional to assure compliance with code, construction, and performance requirements. Because APA has no control over quality of workmanship or the conditions under which engineered wood products are used, it cannot accept responsibility of product performance or designs as actually constructed.